

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01



Test Report

JIS Z 2801:2012 (Mod)

Antimicrobial products – Test for antimicrobial activity and efficacy

Test Object:

*Coated leneta foil against Enterococcus hirae DSM3320
ATCC10541 after one year of artificial aging*

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01

Report on Findings

Client: Nano-Care UK (Signo-Nanocare UK Ltd)
Address: PO Box 225, Oswestry, Shropshire, SY10 1DL, UK +44 1691 654 282

Work order no.: 3223.3_Rev3

Test object: Coated leneta foil against *Enterococcus hirae* DSM3320 ATCC10541 after one year of artificial aging

Sample description: painted plastic films

Date of receipt of sample: 2018-Oct-22

Type of test: JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy

Test Germ: *Enterococcus hirae* DSM3320 ATCC10541

Test laboratory: QualityLabs BT GmbH

Address: Neumeyerstrasse 46a
90411 Nuremberg, Germany

Setup-Code: 190109-10290-2801-01

Sample material: Leneta foil

No. of pages in report: 7

Report on findings to the client: **Place and date of preparation:** Nuremberg, 2019-Feb-27
Recipient: Nano-Care Deutschland GmbH
 replaces the test report from the 20th Jan. 2019

Laboratory Director: _____
 Harald Gerauer, Laboratory Director
 QualityLabs BT GmbH

Released: _____
 Markus Zehe, Managing Director
 QualityLabs BT GmbH

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01

Declaration on Quality Assurance

This investigation was performed and supervised according to the standard operating procedure "SOP zu JIS Z 2801:2012 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

Archiving

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

Test description

Anti-bacterial activity is determined in accordance with a modified version of JIS Z 2801:2012.

During the test, a thin liquid-film containing the bacteria (1.25×10^4 CFU / cm²) is applied directly to the test sample (Standard: 5 cm x 5 cm). To avoid desiccation a foil (Standard: 4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined (t_0 value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined (t_{24} value).

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01

Assessment of antimicrobial activity

A logarithmic germ reduction of **≥ 3 log scales** of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduktion [log scales]	Antibacterial activity
< 3	Not sufficient antimicrobial activity
≥ 3	Sufficient antimicrobial activity

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01

References to Testconditions

Test conditions		
Sample size	25	cm ²
Foil size	16	cm ²
Volume Inoculum	400	μl
Sample cleaning		-

References to deviations, preincubations, special test conditions

The samples have been stored for 56 days at 50 °C, which corresponds to an artificial aging of 1 year according to ASTM F 1980.

Test Report JIS Z 2801:2012 (Mod)

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01

Test Results

Sample Name	Sample Code	t ₀ (cells/cm ²)			t ₂₄ (cells/cm ²)			Reduction [%]	Log Reduction
1 Reference sample	102902310180011	1.1 x 10 ⁵	9.4 x 10 ⁴	1.2 x 10 ⁵	1.3 x 10 ⁵	1.4 x 10 ⁵	7.6 x 10 ⁴		Reference
2 Liquid Guard 2,9%	102902310180012				< 1.0 x 10 ¹	< 1.0 x 10 ¹	< 1.0 x 10 ¹	> 99.99	> 4

*see "Interpretation of Results", page 6

Test strain	<i>Enterococcus hirae</i> DSM3320 ATCC10541
Initial cell count inoculum / cm²	1.25 x 10⁴
Initials of the editor	GM
Measurement ended on	17-01-2019

Work Order	3223.3_Rev3
Setup-Code	190109-10290-2801-01

Comments on test objects

NONE

Interpretation of the results based on the measurements

NONE

Editor: Mr. Shendi_____

Crosschecked: Mr. Mannala _____

References

JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy